

PCT/EP200 4 / 0 0 8 6 8 9

16 AUG. 2004



INVESTOR IN PEOPLE

The Patent Office
Concept House
Cardiff Road
Newport
South Wales
NP10 8QQ

PRIORITY DOCUMENT

SUBMITTED OR TRANSMITTED IN
COMPLIANCE WITH RULE 17.1(a) OR (b)

I, the undersigned, being an officer duly authorised in accordance with Section 74(1) and (4) of the Deregulation & Contracting Out Act 1994, to sign and issue certificates on behalf of the Comptroller-General, hereby certify that annexed hereto is a true copy of the documents as originally filed in connection with the patent application identified therein.

In accordance with the Patents (Companies Re-registration) Rules 1982, if a company named in this certificate and any accompanying documents has re-registered under the Companies Act 1980 with the same name as that with which it was registered immediately before re-registration save for the substitution as, or inclusion as, the last part of the name of the words "public limited company" or their equivalents in Welsh, references to the name of the company in this certificate and any accompanying documents shall be treated as references to the name with which it is so re-registered.

In accordance with the rules, the words "public limited company" may be replaced by p.l.c., plc, P.L.C. or PLC.

Re-registration under the Companies Act does not constitute a new legal entity but merely subjects the company to certain additional company law rules.

Signed

AmBrewer

Dated 10 August 2004

BEST AVAILABLE COPY

Patents Form 1/77

Patents Act 1977
(Rule 16)

The
Patent
Office

4 AUG 2003

LONDON

1/77

The Patent Office
Cardiff Road
Newport
Gwent NP9 1RH

Request for grant of a patent

(See the notes on the back of this form. You can also get an explanatory leaflet from the Patent Office to help you fill in this form)

1. Your reference	3.81584		
2. Patent application number (The Patent Office will fill in this part)	0318257.3		05AUG03 E827741-1 000027 P01/7700 0.00-0318257.3
3. Full name, address and postcode of the or of each applicant (underline all surnames)	Borealis Technology OY PO Box 330 Fin-06101 Porvoo Finland		
Patents ADP number (if you know it)	07914617001		
If the applicant is a corporate body, give country/state of incorporation	Finland		
4. Title of the invention	Nucleating Agent		
5. Name of your agent (if you have one)	Frank B. Dehn & Co.		
"Address for service" in the United Kingdom to which all correspondence should be sent (including the postcode)	179 Queen Victoria Street London EC4V 4EL		
Patents ADP number (if you know it)	166001		
6. If you are declaring priority from one or more earlier patent applications, give the country and the date of filing of the or of each of these earlier applications and (if you know it) the or each application number	Country	Priority application number (if you know it)	Date of filing (day / month / year)
7. If this application is divided or otherwise derived from an earlier UK application, give the number and the filing date of the earlier application	Number of earlier application	Date of filing (day / month / year)	
8. Is a statement of inventorship and of right to grant of a patent required in support of this request? (Answer 'Yes' if: a) any applicant named in part 3 is not an inventor, or b) there is an inventor who is not named as an applicant, or c) any named applicant is a corporate body. See note (d))	Yes		

Patents Form 1/77

9. Enter the number of sheets for any of the following items you are filing with this form. Do not count copies of the same document

Continuation sheets of this form

-

Description 10

Claim(s) 1

Abstract -

Drawing(s) 1

10. If you are also filing any of the following, state how many against each item.

Priority documents -

Translations of priority documents -

Statement of inventorship and right to grant of a patent (Patents Form 7/77) -

Request for preliminary examination and search (Patents Form 9/77) -

Request for substantive examination (Patents Form 10/77) -

Any other documents (please specify) -

11. I/We request the grant of a patent on the basis of this application.

Signature  Date 4 August 2003

12. Name and daytime telephone number of person to contact in the United Kingdom

Neil Campbell
020 7206 0600

Warning

After an application for a patent has been filed, the Comptroller of the Patent Office will consider whether publication or communication of the invention should be prohibited or restricted under Section 22 of the Patents Act 1977. You will be informed if it is necessary to prohibit or restrict your invention in this way. Furthermore, if you live in the United Kingdom, Section 23 of the Patents Act 1977 stops you from applying for a patent abroad without first getting written permission from the Patent Office unless an application has been filed at least 6 weeks beforehand in the United Kingdom for a patent for the same invention and either no direction prohibiting publication or communication has been given, or any such direction has been revoked.

Notes

- If you need help to fill in this form or you have any questions, please contact the Patent Office on 0645 500505.
- Write your answers in capital letters using black ink or you may type them.
- If there is not enough space for all the relevant details on any part of this form, please continue on a separate sheet of paper and write "see continuation sheet" in the relevant part(s) of the form. Any continuation sheet should be attached to this form.
- If you have answered 'Yes', Patents Form 7/77 will need to be filed.
- Once you have filled in the form you must remember to sign and date it.
- For details of the fee and ways to pay please contact the Patent Office.

81584.621

Nucleating Agent

5 This invention relates to a new nucleating agent for polyethylene, in particular to the use of high density polyethylene to nucleate lower density polyethylene.

10 Traditionally, the use of nucleating agents with polyethylenes was not required. Polyethylenes were often produced using Ziegler-Natta catalysts which give rise to polyethylenes with relatively broad molecular weight distributions and broad comonomer distributions which normally did not require nucleating agents.

15 More recently, single site catalysts, e.g. metallocene catalysts, have been employed in the manufacture of polyethylene polymers and these catalysts tend to give polymers having very much narrower molecular weight distributions and comonomer distributions.

20 Hence, when crystallisation begins, almost all the polymer molecules are capable of crystallising at the same temperature causing a large heat of crystallisation and a reduced cooling rate. The result of this is the formation of large spherulites or other crystal domains which cause increased haze and a corresponding lack of transparency. This is a particular problem for film technology where transparency is vital.

25 To overcome this problem nucleating agents have been added to polymer melts. Nucleating agents are chemical substances which when incorporated into a polymer form nuclei for the growth of crystals in the polymer melt. In polypropylene, for example, a higher degree of crystallinity and more uniform crystalline structure is obtained by adding a nucleating agent such as adipic and benzoic acid or certain of their metal salts.

Nucleating agents are designed to improve crystallisation behaviour in processing, i.e. cycle time or line speed, as well as crystallinity and morphology in the final product thereby improving optical and mechanical properties.

Thus it is known to add nucleating agents such as aluminium salts or sodium salts of aromatic carboxylic acids, e.g. sodium benzoate to a polymer melt to increase transparency and reduce haze.

In EP-A-206515, vinylcycloalkane is suggested as a nucleating agent for polypropylene. In JP 58149942; a higher melting point polybutylene terephthalate has been used as a nucleating agent for a lower melting point polybutylene terephthalate without impairing its physical properties or heat cycle resistance.

It has now been surprisingly found that low density polyethylene polymers, e.g. polymers such as linear low density polyethylene (LLDPE), copolymers or terpolymers of ethylene can be nucleated by using other, preferably higher density polyethylenes. Surprisingly, this has been found to result in a reduction in haze and an increase in gloss.

Hence, viewed from one aspect the invention provides the use of a polyethylene polymer, preferably a polyethylene homopolymer, having a density of at least 950 kg/m³ as a nucleating agent for a polyethylene polymer having a density of less than 940 kg/m³, said polymer being, for example, a copolymer or terpolymer of ethylene with at least one C₃₋₁₀ α -olefin.

In a first aspect of the invention, the polymer to which the nucleating agent is to be added (the base polymer) is preferably an ethylene copolymer with a C₃₋₁₀ α -olefin, e.g. propylene, butene, hexene or octene (especially an ethylene/butene or ethylene/hexene copolymer) or an ethylene terpolymer with at least two C₃₋₁₀ α -olefins, preferably selected from propylene, butene, hexene or octene (especially an

ethylene/butene/hexene terpolymer). The polymer to which the nucleating agent is being added should have a density of less than 940 kg/m³, preferably have a density of less than 935 kg/m³, more preferably less than 927 kg/m³, especially less than 920 kg/m³.

The amount of comonomer present in the polymer may vary but is preferably in the range 0.5 to 15% wt, e.g. 2 to 10 %wt.

The polymer to which the nucleating agent is added should preferably be bimodal (or multimodal), i.e. its molecular weight profile does not comprise a single peak but instead comprises the combination of two or more peaks (which may or may not be distinguishable) centred about different average molecular weights as a result of the fact that the polymer comprises two or more separately produced components.

The polymer is preferably manufactured using single site catalyst technology as is well known in the art. Thus, for example, bimodal ethylene polymers may be prepared by two or more stage polymerization or by the use of two or more different polymerization catalysts in a one stage polymerization. Preferably however they are produced in a two-stage polymerization using the same catalyst, e.g. a metallocene catalyst, in particular a slurry polymerization in a loop reactor followed by a gas phase polymerization in a gas phase reactor. A loop reactor - gas phase reactor system is marketed by Borealis A/S, Denmark as a BORSTAR reactor system.

The single site catalyst is preferably a catalyst comprising a metal coordinated by one or more η -bonding ligands. Such η -bonded metals are normally referred to as metallocenes and the metals are typically Zr, Hf or Ti, especially Zr or Hf. The η -bonding ligand is typically an η^5 -cyclic ligand, i.e. a homo or heterocyclic cyclopentadienyl group optionally with fused or pendant substituents. Such metallocene catalysts have been widely described in the scientific

and patent literature for about twenty years. Such metallocene catalysts are frequently used with catalyst activators or co-catalysts, e.g. alumoxanes such as methylaluminoxane, again as widely described in the literature. A preferred catalysts include bis(n-butylcyclopentadienyl) hafnium dibenzyl or rac-ethylene-bis(2-tertbutyldimethylsiloxyindenyl) zirconium dichloride.

The MFR₂ of the polymer to which the nucleating agent is added is generally low, e.g. in the range 0.1 to 10, e.g. 0.5 to 5 g/10min. Its molecular weight distribution (MWD) is preferably 2.5 to 10, especially 3.0 to 8.0. The weight average molecular weight (Mw) of the polymer is preferably between 50,000 and 250,000 g/mol. The polymer acting as the nucleating agent is a high density polyethylene preferably an ethylene homopolymer. The nucleating polymer may be prepared using Ziegler-Natta catalysis or single site catalysis.

The expression "homopolymer" of ethylene used herein refers to a polyethylene that consists substantially, i.e. at least 98% by weight, preferably at least 99% by weight, more preferably at least 99.5% by weight, most preferably at least 99.8% by weight, of ethylene.

The nucleating polymer should have an MFR₂ in the range 0.1 to 1000, preferably 1 to 100, especially 5 to 20. Its density should exceed 950 kg/m³, more preferably 955 kg/m³, especially 960 kg/m³.

It is surprising that the incorporation of a higher density and hence higher crystallinity polyethylene to a lower crystallinity polymer can still give rise to less hazy material. Higher crystallinity polymer tends to be associated with more haze however, in the present invention the total haze of the polymer mixture is less than what would be expected by partial summation.

Conveniently, the polymer to be used as the nucleating agent is unimodal and is made in a slurry or

gas phase polymerisation. Its MWD should be between 2 and 20, preferably 2 to 10, with an MW of approximately 20,000 to 500,000 D, e.g 50,000 to 200,000 D.

5 The polymer is preferably manufactured using a single site or Ziegler-Natta catalyst which are well-known and are widely described in the literature. Their use is commonplace to the skilled polymer chemist.

The amount of nucleating agent required in the invention may vary but is preferably between 0.2 to 30%
10 by weight, more preferably between 0.4 to 15% by weight, e.g. 0.6 to 5% wt relative to the total amount of polyethylene polymer present.

The nucleating agent and polymer may be mixed in any convenient fashion, e.g. compounding, blending,
15 coextrusion etc although dry blending is preferred. Alternatively, the nucleating polymer may be prepared in a polymerisation stage prior to a polymerisation stage where the base polymer is formed. The nucleating polymer could also be made simultaneously with the base
20 polymer by a catalytic site.

The combination of a higher density polyethylene polymer with a lower density polyethylene forms a further aspect of the invention. Hence, viewed from a further aspect the invention provides a polymer
25 composition comprising:

A) less than 5% wt (e.g 0.5. to 5 % wt) of a polyethylene homopolymer having a density of at least 950 kg/m³; and
30

B) at least 95% wt of a polyethylene co- or terpolymer with at least one C₃₋₁₀ α -olefin made by single site catalysis, said polymer having a density of less than 940 kg/m³.

35 The resulting polymer mixture may be used in injection moulding, blow moulding, extrusion coating etc but is of particular value in film technology. The use

of the nucleating agent reduces haze and increases gloss giving rise to improved transparency. Transparent films are of particular use in the medical and food industries where the avoiding the use of other nucleating agents is advantageous since such agents may not be licensed for food contact.

Viewed from another aspect therefore the invention provides a film comprising a polymer composition as hereinbefore described.

Where films are to be used for packaging certain products, in particular foodstuffs, it is especially important that the film has high clarity and gloss. Where films are made only of SSC polymers (i.e. polymers produced using single site catalysts), they often are relatively hazy and/or matt in appearance. It has also been surprisingly found that this can be addressed by blending in with the SSC polyethylene an LDPE, e.g. such that up to 8% wt, more preferably 2 to 7% wt, especially about 5% wt, particularly about 3.5% wt of the polymer blend is the LDPE. Surprisingly we have also found that LDPE of relatively high density, e.g. 925 to 932 kg/m³, is particularly effective in this regard. An example of such an LDPE is available commercially from Borealis A/S under the trade name Himod LDPE which is produced by tubular high pressure processes.

This effect of the relatively high density LDPE on optical properties of PE film is quite unexpected as it would have been expected that the higher the density of the LDPE additive the less the improvement in optical properties would be. Accordingly, viewed from a further aspect the invention provides the use of a relatively high density LDPE, e.g. having a density of 925 to 932 kg/m³, as an additive in a polyethylene composition (e.g. as 1 to 5% wt of the composition) for film production to improve the optical characteristics of the film produced therefrom.

Films may be prepared using conventional film

production techniques. The film will typically be 10 to 300 μm in thickness, especially 15 to 100 μm . The specific thickness will be selected according to the nature of the product to be packaged by the film and its expected subsequent handling conditions.

The films however are preferably extruded, particularly preferably with a blow up ratio of 2:1 to 4:1.

If desired the film may be multilayered, e.g. as a result of lamination or coextrusion.

The invention will now be described with reference to the following non-limiting examples and figures 1 to 3 which show crystallisation on-set temperatures for the mixtures in Example 2.

Experimental

MFR

MFR was measured according to ISO 1133 at 190°C. The load has been indicated as a subscript, i.e. MFR_2 denotes the measurement has been carried out under a load of 2.16 kg and MFR_{21} denotes the measurement has been carried out under a load of 21.6 kg, respectively.

MWD:

The weight-average molecular weight M_w , and the molecular weight distribution ($\text{MWD} = M_w/M_n$, where M_n equals number-average molecular weight) is measured by a method based on ISO/TC61/SC5 N 5024. The main difference between this method and the method used is the temperature; the ISO method being at room temperature while the method used being at 140°C. The ratio of M_w and M_n is a measure of the broadness of the distribution, since each is influenced by the opposite end of the "population".

Density:

Density is measured according to ISO 1183/D.

5 **Polymer Preparation:**

10 Polymer A is Component A prepared according to Example 1 of WO02/070602. Polymer A is an ethylene homopolymer made using bis(n-butyl-Cp)ZrCl₂ and MAO having a density of 957, Mw of 77,000 D, and MWD of 2.7.

15 The polyethylene base polymers B and C were prepared in a bimodal two stage reactor under the following conditions: (The catalyst used for polymer B was bis(n-butylcyclopentadienyl) hafnium dibenzyl and for polymer C was rac-ethylene-bis(2-tertbutyldimethylsiloxyindenyl) zirconium dichloride.

	Polymer B	Polymer C
20 Loop		
Comonomer	C4	C4
MFR2	100	119
density	937	937
Temp.	85	85
25 Pressure (Bar)	60	60
H2/C2 (mol/kmol)	0.33	0.55
C4/C2	139	182
[C2] mol%	6.6	

	GPR	Polymer B	Polymer C
	Comonomer	C6	C4
	Temp	80	75
5	C2 mol%	25	52
	C6/C2 mol/kmol	14	
	C4/C2 mol/kmol		68
	H2/C2 mol/kmol	0.35	0.00
	Split	50/50	49/51
10	Mw D		113000
	MWD		4.4

MG9647A is a commercially available polymer grade from Borealis A/S.

Example 1

Polymers used in blending trials:

	Material		MFR2	d
	Polymer B	Bimodal SSC terpolymer	1.3	918
20	MG9647A	Unimodal Z-N polymer from Gas Phase reactor	8	964

Polymers were dry blended (not compounded) and 40 µm films were produced on an ANKUTEC film line (50 mm die diameter, die gap: 2.1 mm), BUR: 2.5 , Temp.: 210°C)

Haze and Gloss of the produced film were measured according to ASTM D 1003 and ASTM D 523-66T.

30		Haze(%)	Gloss
	Pure Polymer B	48,6	23,8
	Poly B + 0,5% MG9647A	35,2	38,5
	Poly B + 1 % MG9647A	38,8	48,9
	Poly B + 3 % MG9647A	31,0	68,3

Conclusion: Significant improvement in optical properties by blending small amounts of Z-N HDPE.

Example 2

5

Material		MFR2	d
Polymer C	Bimodal LLD	1.5	920
Polymer A	Homopolymer	6.5	958

10 Materials were compounded at 200°C in A Midi 2000 machine. Compounding time was 3 minutes. Respectively, 0.5, 2 and 5% of A was blended into polymer C. The extrudate was then used to press films of thickness approximately 180 μm in a hot stage.

15

DSC Analysis

20 Samples of equal size were cut from pressed films, sample mass around 5 mg. Heating and cooling rates were 10 K/min. Melting peaks of Polymer C and Component A were 115.9 and 131.7°C respectively. Figures 1 to 3 show variations of crystallisation onset and peak temperatures as a function of the percentage of A in the blend.

25

The figures reflect a nucleation effect.

Claims

1. Use of a first polyethylene polymer having a
5 density of at least 950 kg/m³ as a nucleating agent for a
second polyethylene polymer having a density of less
than 940 kg/m³.
2. Use of claim 1 wherein said first polyethylene
10 polymer is a homopolymer.
3. Use as claimed in claim 1 or 2 wherein said second
polyethylene polymer is a copolymer or terpolymer of
ethylene with at least one C₃₋₁₀ α -olefin.
15
4. A polymer composition comprising:

A) less than 5% wt of a polyethylene homopolymer
having a density of at least 950 kg/m³; and
20
B) at least 95% wt of a polyethylene co- or terpolymer
with at least one C₃₋₁₀ α -olefin, said polymer having a
density of less than 940 kg/m³.

Crystallisation on-set temperature
Polymer C with Polymer A




Figure 1

Crystallisation peak temperature
Polymer C with Polymer A




Figure 2

Crystallisation on-set temperature
Polymer C with Polymer A





Fig. 3

NRJ
PCT/EP2004/008689



**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

☐ BLACK BORDERS

☒ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES

☒ FADED TEXT OR DRAWING

☒ BLURRED OR ILLEGIBLE TEXT OR DRAWING

☐ SKEWED/SLANTED IMAGES

☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS

☐ GRAY SCALE DOCUMENTS

☐ LINES OR MARKS ON ORIGINAL DOCUMENT

☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY

☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.